

Dense Graded Aggregate	
Passing	Percent
1"	100
3/4"	70-100
3/8"	50-80
#4	35-65
#10	25-50
#40	15-30
#200	5-15

CLASS I SAND	
3/8"	100
#4	90-100
#8	75-95
#16	40-80
#50	5-35
#100	0-15
#200	0-10

NO. 610	
1 1/2"	100
1"	85-95
1/2"	40-75
#4	15-40
#100	0-10

NO. 810	
3/4"	100
1/2"	80-95
#4	25-60
#100	0-10

NO. 7	
1"	100
3/4"	85-95
3/8"	30-65
#4	5-25
#8	0-5

NO. 9	
1/2"	100
3/8"	80-95
#4	10-30
#8	0-5

NO. 710	
1"	100
3/4"	80-95
3/8"	30-75
#4	0-20
#100	0-10

NO. 10	
3/8"	100
#4	75-100
#16	30-45
#100	5-15

NO. 8	
3/4"	100
1/2"	80-95
3/8"	40-65
#4	5-20
#8	0-5

NO. 11	
3/8"	100
#4	40-90
#8	10-40
#100	0-5

MORTAR SAND	
#8	100
#50	10-40
#100	0-10

CONCRETE SAND	
3/8"	100
#4	85-100
#16	40-80
#50	5-25
#100	0-5